

# Clay Types

112 **Speckled Brown Stoneware** Δ 4 - 6

Plastic clay for wheel throwing and modeling. Granular manganese creates speckles.  
Δ 6 shrinkage: 11%

182 **White Stoneware** Δ 6 - 10

Near white plastic stoneware. Good for use with bright glazes. Contains small amount of fine grog.  
Δ 6 shrinkage: 11%

306 **Light Brown Stoneware** Δ 6 - 10

Smooth throwing body. Orange brown in gas firing.  
Δ 6 shrinkage: 12.5%

259 **Medium/Dark Stoneware** Δ 6 - 10

Warm red-brown in gas firing. Paler in electric firing.  
Δ 6 shrinkage: 12.5%

308 **Dark Red "Brooklyn" Stoneware** Δ 6 - 8

Red stoneware body with sand and grog. Electric firing yields red at Δ 4, deep sand at Δ 8  
Δ 6 shrinkage: 12.5%

257 **Porcelain** Δ 8 - 10

A porcelain body with a fine white marble-like quality. White, tight, and translucent when thin.  
Δ 8 shrinkage: 13.5%

**B Mix (porcelaineous stoneware)** Δ 5

Cream-white clay that is easy to throw and form. Similar to porcelain, with a smooth texture.  
Fires grey/white in reduction and lighter in oxidation.  
Δ 6 shrinkage: 12%

420 **Sculpture Clay** Δ 2 - 6

Our most heavily grogged body, formulated for sculpture. Sand color at Δ 6.  
Δ 6 shrinkage: 8%

104 **Low-Fire Red Clay** Δ 06 - 4

Versatile clay with fine grog. Use for handbuilding and wheel throwing  
Δ 06 shrinkage: 6%